

19



Europäisches Patentamt
European Patent Office
Office européen des brevets

11 Publication number:

**0 293 795
A1**

12

EUROPEAN PATENT APPLICATION

21 Application number: **88108577.3**

51 Int. Cl.4: **A61K 7/48 , A61K 7/02**

22 Date of filing: **28.05.88**

A Request pursuant to Rule 88 EPC has been filed to correct the applicant from "General Electric Company" in "Toshiba Silicone Co., Ltd."

30 Priority: **29.05.87 JP 131349/87**

43 Date of publication of application:
07.12.88 Bulletin 88/49

64 Designated Contracting States:
DE FR GB IT

71 Applicant: **GENERAL ELECTRIC COMPANY**
1 River Road
Schenectady New York 12305(US)

72 Inventor: **Yonekura, Kazuya**
2-31, Roppongi 6-Chome
Minato-ku Tokyo 106(JP)
Inventor: **Dalkuzono, Shoji**
2-31, Roppongi 6-Chome
Minato-ku Tokyo 106(JP)

74 Representative: **Schüler, Horst, Dr. et al**
Kaiserstrasse 69
D-6000 Frankfurt/Main 1(DE)

54 **Makeup or cosmetic composition.**

57 There are disclosed makeup or cosmetic compositions comprising polymethylsilsesquioxane powders.

EP 0 293 795 A1

MAKEUP OR COSMETIC COMPOSITIONS

The present application claims the priority of Japanese Patent Application Serial No. 62-131349 filed on May 29, 1987.

BACKGROUND OF THE INVENTION**FIELD OF THE INVENTION**

The present invention relates to makeup and cosmetic compositions. More particularly, the present invention relates to makeup and cosmetic compositions which provide for smooth application and are pleasant to the touch.

STATEMENT OF THE PRIOR ART

In general, makeup and cosmetic compositions are basically composed of components such as oils, powders, water soluble bases, etc. Further, such composition come in a variety of forms such as solid foundation, including solid eye shadows and lipsticks, or liquid emulsion type and cream emulsion type foundations, etc.

A variety of powders are used in makeup and cosmetic compositions for art known purposes. Talc, kaolin, zinc white, titanium white, calcium carbonate or magnesium carbonate are effectively employed as loading pigments. Inorganic pigments include titanium white, zinc white, carbon black, iron tetratrioxide, yellow ochre, red iron oxide, amber, ultramarine, etc. Organic pigments having a strong coloring property are also employed in powder form. Additional powders generally employed in makeup and cosmetic compositions include zinc stearate, magnesium stearate, starch, silica powders, bentonite, etc.

As the prior art using specific powder components, there are known cosmetic compositions in which organic synthetic resin powders are incorporated as loading pigments or modifiers to improve clearness of hue, coloring, transparency, etc. (cf. Published Unexamined Japanese Patent Application No. 99236/1977). Also known are cosmetic compositions in which organo-polysiloxane cured powders obtained by grinding an organo-polysiloxane elastomer or organo-polysiloxane resin are used to improve application (cf. Published Unexamined Japanese Patent Application No. 194009/1986). However, in the former case, it is desirable to improve the natural appearance of the color. In the latter case, the cured rubber or resin is pulverized to a powder having an irregular broad particle size distribution which is too broad and is extremely difficult to control. Thus, smoothness of makeup or cosmetic compositions containing these powders upon application is insufficient.

SUMMARY OF THE INVENTION

An object of the present invention is to provide makeup or cosmetic compositions which eliminate the foregoing problems in the prior art and can provide extreme smoothness upon application and impart natural color.

As a result of extensive investigations to achieve the object described above, the present inventors have found that by using polymethylsilsesquioxane powders as a powder component of makeup or cosmetic compositions, excellent effects of natural color and smoothness upon application, etc. are gained. Thus, the present invention relates to makeup or cosmetic compositions characterized by containing polymethylsil-sesquioxane powders.

DETAILED DESCRIPTION OF THE INVENTION

Polymethylsilsesquioxane powders are the characteristic component in the present invention that contribute to smooth application of makeup or cosmetic compositions to the skin, to a moisturized feeling and to more enhanced functions of pigment powders used as a cosmetic component in combination therewith.

Such polymethylsilsesquioxane powders can be obtained by any of several methods. There is a method which comprises either hydrolyzing methyl trichlorosilane while spraying it or dropwise adding methyl trichlorosilane in large amounts of water to cause hydrolysis and condensation (cf. Belgian Patent No. 572,412). There is a method which comprises hydrolyzing and condensing methyl trialkoxysilanes, etc. in an aqueous solution containing alkali metal carbonates or alkaline earth metal hydroxides (cf. Published Unexamined Japanese Patent Application No. 72300/1979). There is also a method which comprises hydrolyzing and condensing methyl trialkoxysilanes, etc. in an aqueous solution of ammonia or amines (cf. Published Unexamined Japanese Patent Application No. 13813/1985), etc. Of these methods, the polymethylsilsesquioxane powders obtained by the method of Published Unexamined Japanese Patent Application No. 13813/1985 is preferred to achieve the object of the present invention, because the powders have a small chlorine content, are free from alkali metals or alkaline earth metals and have excellent free fluidity. In addition and regardless of the method of manufacture, it is preferred that the shape of the polymethylsilsesquioxane powders be independent and substantially spherical and that more than 80% of the whole particles be within the range of $\pm 30\%$ of a mean particle diameter in the particle size distribution.

The mean particle diameter of the polymethylsilsesquioxane powders is preferably 0.05 to 100 μm , more preferably 0.1 to 20 μm . In case that the particle diameter is too small, it is difficult to prepare them. Further in case that the particle diameter is too large, it is not only difficult to prepare but also it is difficult to achieve the object of the present invention.

The amount of the polymethylsilsesquioxane powders to be formulated can vary depending upon the form of the particular cosmetic under manufacture and is not particularly limited. However, it is preferred that the powders be incorporated, for example, in the case of press type makeup cosmetic compositions, in the range of from 1 to 60 wt% and, in the case of liquid makeup cosmetic compositions in the range of from 0.1 to 40 wt%.

The makeup cosmetic composition of the present invention can be prepared by formulating the polymethylsilsesquioxane powders and other cosmetic powdery raw materials in cosmetic binder oil and dispersing them homogeneously. As the other cosmetic powdery raw materials, there can be used leading pigments such as talc, kaolin, zinc white, magnesium carbonate, calcium carbonate, silica powders, starch, metal salts of higher fatty acid, silk powders, bentonite, etc.; inorganic pigments having various colors such as titanium white, zinc white, carbon black, iron tetratrioxide, yellow ocher, red iron oxide, amber, ultramarine, etc.; organic color pigments such as tar pigment, β -carotin, safflower pigment, chlorophyll, cochineal, etc.; and pearl pigments such as mica titanium, etc.

As the cosmetic binder oil, there can be used those conventionally employed, for example, liquid paraffin, vaseline, beeswax, microcrystalline wax, olive oil, stearic acid, castor oil; higher alcohols such as octyl alcohol, hexadecyl alcohol, etc.; lower alcohols such as ethanol, etc.; esters, higher fatty acids, etc. In addition, there may also be used siloxanes such as polydimethylsiloxane, polymethylphenylsiloxane, etc.

If necessary, water, surface-active agents, perfume, thickeners, antiseptics, etc. can also be formulated in the makeup or cosmetic composition of the present invention.

The makeup or cosmetic composition of the present invention contains the polymethylsilsesquioxane powders and can thus provide an extremely smooth application and impart favorable natural color.

EXAMPLES OF THE INVENTION

Hereafter the present invention will be described with reference to the examples, wherein "parts" are "parts by weight".

Synthesis Example 1

In a four-necked flask equipped with a thermometer, a reflux condenser and stirrer, 500 parts of water and 50 parts of 28% ammonium aqueous solution were charged. Then, 200 parts of methyl trimethoxysilane were added dropwise to the ammonia aqueous solution over 40 minutes with stirring. The reaction temperature started from 10°C and reached 30°C upon completion of the dropwise addition. Next, the system was heated with a mantle heater to reflux at 84°C. Stirring was continued for about an hour at this temperature. After cooling, the precipitated product in the flask was collected, washed with water and dried. Then, via a pulverizing step, polymethylsilsesquioxane powders having a mean particle diameter of 2 μm, having a particle diameter of 1.7 to 2.1 μm in more than 99% of the whole particles and having excellent free fluidity were obtained.

Synthesis Example 2

In a four-necked flask equipped with a thermometer, a reflux condenser and stirrer, 4,000 parts of water and 50 parts of 28% ammonium aqueous solution were charged. The mixture was stirred at 100 r.p.m. for 10 minutes to make a homogeneous ammonia aqueous solution. Then, 600 parts of methyl trimethoxysilane having a chlorine content of 10 ppm calculated as a chlorine atom were rapidly added to the ammonia aqueous solution, while rotating the stirrer at 5 r.p.m., to form two phases. The methyl trimethoxysilane phase formed the upper layer and the ammonia aqueous solution phase formed the lower layer. Then, the stirring rate of the stirrer was changed to 20 r.p.m. and hydrolysis and condensation were allowed to proceed at the interface between the methyl trimethoxysilane and the ammonia aqueous solution, while maintaining the two phase state. As the reaction proceeded, the reaction product gradually precipitated in the lower layer. The lower layer turned white and became turbid because of the suspension of the reaction product. The methyl trimethoxysilane phase in the upper layer became thinner and disappeared in about 3 hours (confirmed by observation with the eye). Subsequently, the temperature was maintained at 50 to 60°C and the system was stirred for 3 hours under the same conditions. Thereafter, the system was cooled to 25°C. Then, after the precipitated product was filtered through a wire gauze of 100 mesh, it was centrifuged to dehydrate, whereby the product was rendered cake like. The cake phase was dried in an oven of 200°C and crushed using a labo jet to give white powders of polymethylsilsesquioxane.

The thus obtained polymethylsilsesquioxane powders were substantially spherical and had a mean particle diameter of about 1.9 μm.

Synthesis Example 3

Spherical polymethylsilsesquioxane powders having a mean particle diameter of about 4.5 μm were obtained in a manner similar to Synthesis Example 1 except that the amount of 28% ammonium aqueous solution was changed to 5 parts and the stirring rate after the system was rendered two phase state was changed to 25 r.p.m.

Example 1

In Container (1) were charged 30 parts of talc, 5 parts of kaolin, 25 parts of sericite, 10 parts of titanium dioxide and 1 part of red iron oxide. While homogeneously mixing them, the mixture was heated at 100°C for 2 hours. In the mixture were formulated 5 parts of polymethylsilsesquioxane powders obtained in Synthesis Example 1 and 5 parts of polyethylene powders. While further pulverizing, they were homogeneously mixed.

On the other hand, 3 parts of polydimethylsiloxane having a viscosity of 100 cSt at 25°C, 4 parts of liquid paraffin, 3 parts of stearyl alcohol, 2 parts of beeswax and 2 parts of squalane were charged in another Container (2). Then the mixture was heated at 100°C for an hour to dissolve homogeneously. Thereafter, the contents of Container (1) and Container (2) were combined and mixed homogeneously. After pulverizing, press molding was performed to give a cosmetic foundation.

Examples 2 and 3

Two kinds of foundations were obtained in a manner similar to Example 1 except that 5 parts of spherical polymethylsilsequioxane powders obtained in Synthesis Examples 2 and 3, respectively were used instead of 5 parts of polymethylsilsequioxane powders obtained in Synthesis Example 1.

Comparative Example 1

A foundation was obtained in a manner similar to Example 1 except that 5 parts of polyethylene powders were used instead of 5 parts of polymethylsilsequioxane powders.

Synthesis Example 4

A mixture of 100 parts of polysiloxane composed of a dimethylsiloxane units end-stopped with dimethylvinylsilyl groups and having a viscosity of 500 cSt at 25°C with 3.5 parts of polymethylhydrogen-siloxane end-stopped with trimethylsilyl groups and having a viscosity of 20 cSt at 25°C was mixed with chloroplatinic acid in an amount of 10 ppm as platinum metal based on the total amount of the mixture and isopropyl alcohol solution. The mixture was heated at 150°C for 2 hours to give rubbery cured product. The cured product was ground into fine powders with an atomizer to give powders having a particle diameter of 1 to 50 μm.

Comparative Example 2

A foundation was obtained in a manner similar to Example 1 except that 5 parts of the powders of Synthesis Example 4 described above were used instead of 5 parts of polymethylsilsequioxane powders obtained in Synthesis Example 1.

Evaluation test

With respect to the 5 cosmetic of foundations obtained in the examples and comparative examples, a use test by application was performed by 10 female panel members. The results are shown in Table 1. Evaluation standards are as follows. Indication is by a mean value

Extremely good = 3, Good = 2, Ordinary = 1

	<u>Table 1</u>			<u>Comparative Example</u>	
	<u>1</u>	<u>Example 2</u>	<u>3</u>	<u>1</u>	<u>2</u>
Spreadability	2.1	2.9	2.8	1.6	2.0
Appearance (color)	2.8	2.9	2.9	1.5	1.7
Feel of application	2.5	3.0	3.0	1.1	1.6

As is evident from the table, the cosmetic compositions of the present invention were evaluated to be extremely good or good.

While the invention has been described in detail and with reference to specific embodiments thereof, it is apparent to one skilled in the art that various changes and modifications can be made therein without departing from the spirit and the scope of the present invention.

Claims

1. A makeup or cosmetic composition comprising polymethylsilsesquioxane powders.
2. A makeup or cosmetic composition as claimed in claim 1 wherein a mean particle diameter of
5 polymethylsilsesquioxane powders is 0.05 to 100 μm .
3. A makeup or cosmetic composition as claimed in claim 1 wherein polymethylsilsesquioxane powders
are spherical.
4. A makeup or cosmetic composition as claimed in claim 1 wherein not smaller than 80% of the whole
particles of polymethylsilsesquioxane powders are within the range of $\pm 30\%$ of a mean particle diameter.
- 10 5. A makeup or cosmetic composition as claimed in claim 1 further comprising cosmetic binder oil.

15

20

25

30

35

40

45

50

55



DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.4)
Y	PATENT ABSTRACTS OF JAPAN, vol. 10, no. 166 (C-353)[2222], 13th June 1986; & JP-A-61 18 708 (POLA KASEI KOGYO K.K.) 27-01-1986 * Abstract *	1-2,5	A 61 K 7/48 A 61 K 7/02
Y,D	PATENT ABSTRACTS OF JAPAN, vol. 9, no. 125 (C-283)[1848], 30th May 1985, page 129 C 283; & JP-A-60 13 813 (TOUSHIBA SILICONE K.K.) 24-01-1985 * Abstract *	1-2,5	
Y,D	PATENT ABSTRACTS OF JAPAN, vol. 11, no. 18 (C-398), 17th January 1987, page 74 C 398; & JP-A-61 194 009 (TORAY SILICONE CO., LTD) 28-08-1986 * Abstract *	1-2,5	
A	EP-A-0 090 577 (DOW CORNING CORP.) * Whole document *	1,5	
A	US-A-3 824 303 (LANZET et al.) * Column 3, line 45 - column 4, line 33; example 7; claims *	1,5	TECHNICAL FIELDS SEARCHED (Int. Cl.4) A 61 K
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 07-09-1988	Examiner FISCHER J.P.
CATEGORY OF CITED DOCUMENTS X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document			